

# Lanopro Coating 10-15 G

## Coating



Product Data Sheet - 2010.12.06

### APPLICATION

Apply with a soft bristle brush or broom, a long nap roller, or suitable spray equipment. Using an airless spray system is recommended (Lanopro can offer spray equipment on request). The coating can be used on both wet and dry surfaces. Under cold (<5°C) conditions it is beneficial to heat the product (25°C to 35°C is the ideal temperature) for better flow and spray ability. Coverage rates will vary depending on porosity of surface as well as speed of the application. Avoid apply unless temperature is 5°C or higher (refer to heating of the coating).

### Physical and Chemical Data

Analysis	Method	Unit	Results
Form			Thin Liquid
Viscosity at 40°C	ASTM-D445		42.28 cSt
Density at 20°C	ASTM-D1298	kg/m <sup>3</sup>	921.1
Flash Point		°C	288
Colour			Light Brown
Copper Strip Corrosion	ASTM-D4048		1a
Odour			Faint or none

The product is non-toxic and has no negative environmental impact. It is approved for use in marine environments by Harmonized Offshore Chemical Notification Format (HOCNF). Use normal protective goggles to protect eyes. It is not necessary to take any special precautions for workers that use this product. See Material Safety Data Sheets (MSDS) for more information.

### Handling

- **Storage** Storage temperatures (0°C to +40°C)
- **Packaging** 1L - 5L - 20L - 196L drums and 1000L IBC tank. Bulk on request.

ID No: D 100 110:2

Lanopro Production AS  
Smedveien 7  
1344 Haslum  
Norway

Phone: +47 40 00 15 14  
Fax: +47 21 54 73 43  
E-mail: [mail@lanopro.com](mailto:mail@lanopro.com)  
[www.lanopro.com](http://www.lanopro.com)

Lanopro Pte Ltd  
112 Robinson Road  
#12-01  
Singapore 068902

Phone: +65 6222 3209  
Fax: +65 6826 4109  
E-mail: [mail@lanopro.com](mailto:mail@lanopro.com)  
[www.lanopro.com](http://www.lanopro.com)