

Lanopro Coating 10-05 AFD

Dry Coating



Specification Sheet - 2011.01.20

DESCRIPTION

Lanopro Coating 10-05 AFD is a premium grade coating designed for maximum protection against degradation and corrosion of the steel. It is a coating that is recommended in areas where a dry surface is needed ie. dusty areas or in transport on trucks etc. It is suitable as a replacement for petroleum based or other environmental hazard coatings. The product forms a dry protective shield which protects against harsh conditions and corrosion. The coating will not crack or peel, and will prevent mildew while offering unbeatable weather-proof protection and excellent resistance under the most demanding weather conditions. Dry time is normally 5 to 8 hours in 20°C.

SURFACE PREPARATION

All surfaces must be free of dust, oil, gravel, or peeling paint and all other foreign matters. However, the product may be applied on rusty metal without any primer or brushing. Prior pressure washing of the surfaces is recommended for optimal results. All surfaces should be thoroughly rinsed prior to applying the coating.

APPLICATION

It is recommended to be stirred before use. Apply with a soft bristle brush or broom, a long nap roller, or suitable spray equipment. Using an airless spray system is recommended. The coating can be used on both wet and dry surfaces. Coverage rates will vary depending on porosity of surface. Recommended application is one or two single coatings, depending on how long the protective shield should last and environment. During application, keep tools clean and free from build-up by frequent rinsing with hot water. Adequate protection for most surfaces is obtained by the use of 0.1 litre of per m². Do not apply unless temperature is 5°C or higher (refer to heating of the coating).

CLEAN UP

Clean brushes, tools and other equipment with soapy and hot water after use. Dried film require warm water pressure cleaning. **Lanopro Heavy Cleaner 84-01** is also recommended as it is an environmental friendly degreaser.

PHYSICAL PROPERTIES

See Material Safety Data Sheets (MSDS) for more information.

Copyright © 2009 – Lanopro Pte Ltd

ID No - S 100 109:4

Lanopro Production AS
Smedveien 7
1344 Haslum
Norway

Phone: +47 40 00 15 14
Fax: +47 21 54 73 43
E-mail: mail@lanopro.com
www.lanopro.com

Lanopro Pte Ltd
112 Robinson Road
#12-01
Singapore 068902

Phone: +65 6222 3209
Fax: +65 6826 4109
E-mail: mail@lanopro.com
www.lanopro.com